

**PRODUCTION OF EXTERIOR MATERIAL OF BUILDING STRUCTURE  
COMPRISING FLY ASH AS RAW MATERIAL AND EXTERIOR MATERIAL**

**Patent number:** JP2217355  
**Publication date:** 1990-08-30  
**Inventor:** HACHIMAN YASUHIRO  
**Applicant:** YASUHIRO HACHIMAN  
**Classification:**  
- **International:** C04B35/10; C04B35/00  
- **European:**  
**Application number:** JP19890037253 19890216  
**Priority number(s):**

**Abstract of JP2217355**

**PURPOSE:** To inexpensively obtain the title lightweight exterior material by blending granulated materials comprising fly ash with water, a polymer-based binder with perlite and glass powder, molding into blocks and calcining.

**CONSTITUTION:** (A) Fly ash is blended with (B) 15-20wt.% water and (C) 0.1-1.0wt.% a polymer-based binder, kneaded and granulated to give granulated materials. The granulated materials are mixed with (D) 2-8wt.% perlite and (E) 5-8wt.% glass powder, kneaded and molded by vibration molding or extrusion molding into flat plate shape or brick shape to give blocks. Then the blocks are glazed and calcined at 1,000-1,250 deg.C to give the title exterior material.

---

Data supplied from the **esp@cenet** database - Patent Abstracts of Japan